

High Thermal Conductive Soft Pad with Low Compression Set Property

TC-SET4-20

TC-SET4-20 is a high thermal conductive silicone soft pad with low compression set property while maintaining the flexibility of low hardness.

1 Features

- 1) High Thermal conductivity, Low thermal resistance
- 2) Excellent compressibility and stress relaxation property
- 3) Excellent workability
- 4) Low compression set compared with conventional soft pad
- 5) Low oil bleed


2 Applications

In-vehicle module which particularly long-term heat cycle reliability and vibration reliability are required


3 General properties

Parameter	Test Method	Grade	TC-SET4-20	TC-CAT-20
Features	—	—	Low compression set	Conventional
Appearance (color)	—	—	Light reddish brown	Gray
Structure	—	—	Single layer	Single layer
Density 23°C	g/cm ³	JIS K 6249	3.2	3.2
Hardness Ascer C	—	JIS K 6249	20	20
Break down voltage	kV/1mm	JIS K 6249	15	15
Thermal conductivity	W/m-K	ISO 22007-2	4.5	4.5
Flame retardancy UL94	—	—	V-0 equivalent	V-0


(Not specified values)



4 Pressure and Thickness




5 Pressure and Thermal Resistance



6 Compression set test



Test Method

- 1) 3 mm thickness pad was cut to 20 x 20 mm size, and sandwiched by polyimide films.
- 2) Pad sample was compressed to 50% thickness (1.5 mm) with compression tool and spacer.
- 3) Sample was put into aging chamber. After aging, sample was taken out.
- 4) Pad sample was released after it returned to room temperature, and the thickness 60 minutes later was measured.



Test Results

TC-SET4-20 shows low compression set property.



7 Handling precautions

- 1) Products should be stored in a dry place out of direct sunlight.
- 2) Avoid contact with residual solvents or oils as they may deteriorate the properties of the product.
- 3) For better results, the substrate surface should be cleaned and dried to remove any dirt, moisture or oils before application.
- 4) Prior to using the product with a thermal interface grease, test a sample with a small amount to determine compatibility.
- 5) Keep out of reach of children.
- 6) Please read the Safety Data Sheets (SDS) before use. SDS can be obtained from our Sales Department.

CAUTION

- The data and information presented in this catalog may not be relied upon to represent standard values. Shin-Etsu reserves the right to change such data and information, in whole or in part, in this catalog, including product performance standards and specifications without notice.
- Users are solely responsible for making preliminary tests to determine the suitability of products for their intended use. Statements concerning possible or suggested uses made herein may not be relied upon, or be construed, as a guaranty of no patent infringement.
- For detailed information regarding safety, please refer to the Safety Data Sheet (SDS).
- The silicone products described herein have been designed, manufactured and developed solely for general industrial use only; such silicone products are not designed for, intended for use as, or suitable for, medical, surgical or other particular purposes. Users have the sole responsibility

and obligation to determine the suitability of the silicone products described herein for any application, to make preliminary tests, and to confirm the safety of such products for their use.

- Users must never use the silicone products described herein for the purpose of implantation into the human body and/or injection into humans.
- Users are solely responsible for exporting or importing the silicone products described herein, and complying with all applicable laws, regulations, and rules relating to the use of such products. Shin-Etsu recommends checking each pertinent country's laws, regulations, and rules in advance, when exporting or importing, and before using the products.
- Please contact Shin-Etsu before reproducing any part of this catalog. Copyright belongs to Shin-Etsu Chemical Co., Ltd.

Shin-Etsu

<https://www.shinetsusilicone-global.com/>

Shin-Etsu Chemical Co., Ltd.
4-1, Marunouchi 1-chome, Chiyoda-ku,
Tokyo, 100-0005 Japan

Silicone Division, Sales and Marketing Department III
Phone : +81-(0)3-6812-2409 Fax : +81-(0)3-6812-2415