

Shin-Etsu Silicone

Silicone Rubber

Performance Test Results

Contents

1 Silicone rubber	
General properties	2
Other properties	5
2 Fluorosilicone rubber	6
3 SEP rubber	7
4 Curing agents	
Types	8
Suitability by application	8
Standard addition quantity	9
5 Standard conditions for compression molding	10
6 Primers	10
7 Coloring agents	10
8 Application examples by industry	11

1. Silicone rubber: general properties

Classification		For general purpose, FDA (21CFR177 2600), BfR								JIS B2401 4-C
Grade		KE-931-U	KE-941-U	KE-951-U	KE-961-U	KE-971-U	KE-981-U	KE-961T-U	KE-971T-U	KE-871C-U
Appearance		Milky white translucent			Grayish white			Milky white translucent		Grayish white
Density 23°C g/cm ³		1.07	1.11	1.14	1.22	1.30	1.42	1.17	1.20	1.29
Williams plasticity (10 min after remix)		160	190	240	280	330	420	280	340	260
Curing agent	Curing agent name	C-8	C-8	C-8	C-8	C-8	C-8	C-8A	C-8	C-8
	Standard addition quantity*1	2.0	2.0	2.0	2.0	2.0	2.0	0.5	2.0	1.0
Linear shrinkage*2 %		4.0	3.9	3.9	3.4	3.0	2.7	3.6	3.4	2.9
Physical strength	Hardness Durometer A	31	43	52	63	71	84	62	71	72
	Tensile strength MPa	4.7	6.5	8.2	7.3	7.5	8.8	9.7	8.8	6.9
	Elongation at break %	480	370	330	320	220	100	310	260	190
	Tear strength crescent piece kN/m	15*3	15*3	23*3	20*3	20*3	8	25*3	25*3	9
Compression set 180°C x 22 h		15	11*4	11*4	11*4	9*4	12*4	11*4	11*4	10
Dielectric breakdown strength Normal state kV		—	23	24	25	25	24	24	23	—
Volume resistivity Normal state TΩ·m		—	7	8	6	3	4	4	4	—

(Not specified values)

Classification		Dynamic fatigue durability		Vibration control		For power connector				Anti-static silicone rubber compound
Grade		KE-9511-U	KE-5151-U	KE-5550-U	KE-501EM-U	KE-7211-U	KE-7212-U	KE-7213-U	X-30-3893-U	KE-9590-U
Appearance		Milky white translucent		Pale yellow	Milky white translucent	Light gray	Gray	Blue-white	Black	Milky white translucent
Density 23°C g/cm ³		1.12	1.10	1.25	1.10	1.15	1.20	1.97	1.09	1.15
Williams plasticity (10 min after remix)		200	170	370	170	220	250	190	290	220
Curing agent	Curing agent name	C-8A	C-8B	C-8	C-15	C-3	C-3	C-8	C-8A	C-8
	Standard addition quantity*1	0.6	1.0	2.0	1.5	1.3	1.3	2.0	1.0	2.0
Linear shrinkage*2 %		3.3	3.9	5.2	3.9	—	—	—	—	3.9
Physical strength	Hardness Durometer A	50	54	52	53	54	58	45	40	51
	Tensile strength MPa	6.6	7.7	9.3	7.7	11.0	9.2	2.5	7.4	8.8
	Elongation at break %	310	450	730	520	780	680	320	680	400
	Tear strength crescent piece kN/m	6	15	38	19	31	35	8	26	22*3
Compression set 180°C x 22 h		8	20	13	22	9	10	—	17	14*4
Dielectric breakdown strength kV	Normal state	—	—	—	—	28	28	—	—	22
	Submerged	—	—	—	—	190	100	0.1	—	0.4
Remarks		Middle fatigue durability	High fatigue durability	High decrement	Low motion magnification	Tracking property 3.5 kV	Tracking property 4.5 kV	High dielectricity	Specific resistance 0.2 Ω·m	—

Measurement: in accordance with JIS K 6249 Test pieces: 165°C x 10 min (press cure), 200°C x 4 h (post cure)

(Not specified values)

*1 Standard addition quantity is the quantity of curing agent added to 100 parts compound.

*2 Linear shrinkage values differ according to the curing agent used.

*3 Angle piece

*4 Measured values at 150°C x 22 h.

[Unit conversion] tensile strength: 10 kgf/cm² = 0.98 MPa; tear strength: 1 kgf/cm = 0.98 kN/m; volume resistivity: 10¹⁴ Ω·cm = 1 TΩ·cm.

Classification		For general extrusion molding, FDA, BfR										For tubing			
Grade		KE-541-U*3		KE-551-U*3		KE-561-U*3		KE-571-U*3		KE-581-U*3		KE-153-U	KE-174-U	KE-1551-U*3	KE-1571-U*3
Appearance		Milky white translucent										Milky white translucent			
Density 23°C g/cm ³		1.10		1.14		1.17		1.22		1.24		1.16	1.21	1.16	1.19
Williams plasticity (10 min after remix)		150		200		250		360		430		260	370	270	320
Curing agent	Curing agent name	C-23N	C-25A/B	C-23N	C-25A/B	C-23N	C-25A/B	C-23N	C-25A/B	C-23N	C-25A/B	C-25A/B	C-25A/B	C-23N	C-23N
	Standard addition quantity*1	1.0	0.5/2.0	1.0	0.5/2.0	1.0	0.5/2.0	1.0	0.5/2.0	1.3	0.5/2.0	0.5/2.0	0.5/2.0	0.8	0.7
Linear shrinkage*2 %		—		—		—		—		—		—	—	3.3	—
Physical strength	Hardness Durometer A	40	40	50	50	63	62	70	68	79	77	53	71	56	74
	Tensile strength MPa	8.0	8.2	10.5	9.8	11.5	11.5	11.0	11.0	10.5	10.5	10.0	8.1	10.5	9.5
	Elongation at break %	550	690	530	590	450	470	430	450	310	430	650	520	530	370
	Tear strength crescent piece kN/m	10	22	13	26	15	24	19	26	13	23	36	37	16	23
Compression set 180°C x 22 h		12*4	9*5	8*4	9*5	11*4	9*5	13*4	9*5	14*4	9*5	—	—	—	35*5
Dielectric breakdown strength Normal state kV		—	—	26	—	25	—	26	—	29	—	26	28	28	25
Volume resistivity Normal state TΩ·m		30	—	70	—	300	—	500	—	700	—	900	650	600	600

(Not specified values)

Classification		High strength		Low hardness, high elongation			Flame retardance			
Grade		KE-555-U*	KE-575-U	KE-520-U	KE-530B-2-U	KE-540B-2-U	KE-5620W-U	KE-5620BL-U	KE-5612E-U	KE-5634-U
Appearance		Pale yellow		Milky white translucent			White	Black	Charcoal	Translucent
Density 23°C g/cm ³		1.17	1.21	1.06	1.13	1.13	1.40	1.38	1.49	1.20
Williams plasticity (10 min after remix)		310	320	150	170	180	240	230	230	330
Curing agent	Curing agent name	C-8	C-8	C-8	C-8A	C-15	X-93-1609*6/C-3		C-3	C-25A/B
	Standard addition quantity*1	2.0	2.0	2.0	0.5	1.5	0.3/1.3		1.3	1.0/2.0
Linear shrinkage*2 %		4.0	4.0	4.5	3.8	4.1	3.1	3.2	2.7	3.4
Physical strength	Hardness Durometer A	53	70	23	35	39	59	57	60	70
	Tensile strength MPa	11.0	9.4	5.0	9.7	9.7	6.5	7.0	7.2	7.7
	Elongation at break %	650	550	770	880	700	410	430	290	370
	Tear strength crescent piece kN/m	35	41	10	34	17	12	11	13	14
Compression set 180°C x 22 h		31	18	22	20*5	9*5	21	27	16	20
Dielectric breakdown strength Normal state kV		27	27	—	—	—	27	28	27	29
Volume resistivity Normal state TΩ·m		100	200	—	—	—	50	80	240	300
Flame retardance UL94		—	—	—	—	—	V-0	V-0	V-0	V-1

Measurement: in accordance with JIS K 6249 Test pieces: 165°C x 10 min (press cure), 200°C x 4 h (post cure)

(Not specified values)

*1 Standard addition quantity is the quantity of curing agent added to 100 parts compound.

*2 Linear shrinkage values differ according to the curing agent used.

*3 Test pieces: 120°C x 10 min (press cure), 200°C x 4 h (post cure)

*4 Measured values at 100°C x 22 h

*5 Measured values at 150°C x 22 h

*6 X-93-1609 is a flame retardant.

★ Not available in U.S..

[Unit conversion] tensile strength: 10 kgf/cm² = 0.98 MPa; tear strength: 1 kgf/cm = 0.98 kN/m; volume resistivity: 10¹⁴ Ω·cm = 1 TΩ·cm.

Silicone rubber: general properties

Classification	Heat resistance		Hermetic heat resistance	Steam resistance			Electrically conductive			Heat conductive	
Grade	KE-552-U*3	KE-582-U*4	KE-552B-U*5	KE-7511-U	KE-7611-U	KE-7711-U	KE-3601SB-U	KE-3711-U	KE-3801M-U	KE-6801-U*3	
Appearance	Light brown		Pale yellow	Pale yellow			Black			Dark blue	
Density 23°C g/cm ³	1.16	1.25	1.17	1.14	1.15	1.21	1.17	1.14	1.20	1.90	
Williams plasticity (10 min after remix)	270	470	280	220	220	230	450	480	630	500	
Curing agent	Curing agent name	C-23N	C-23N	C-23N	C-15	C-8A	C-8A	C-8A	C-8A	HC-101/CAT-PL-2	C-23N
	Standard addition quantity*1	1.0	1.0	1.0	1.3	0.6	0.6	1.0	1.0	2.7/0.1	0.8
Linear shrinkage*2	%	2.7	3.3	2.4	3.8	3.9	3.9	4.2	—	—	—
Physical strength	Hardness Durometer A	52	80	52	55	61	72	62	66	73	85
	Tensile strength MPa	10.0	7.0	9.8	9.5	9.1	8.8	7.0	6.5	5.3	4.0
	Elongation at break %	550	250	550	410	330	300	290	170	190	110
	Tear strength crescent piece kN/m	15	20	14	12	11	15	10	—	15*6	—
Compression set 180°C x 22 h	18*7	23	24*7	9	9	10	—	12	18*7	—	
Dielectric breakdown strength Normal state	kV	27	25	28	—	—	—	—	—	26	
Volume resistivity Normal state	TΩ·m	900	900	500	—	—	—	0.05*8	0.05*8	0.03*8	30

(Not specified values)

Classification	For industrial rollers		For electric wire			Fire resistance	Voltage resistance	Oil bleed		Low temperature	Super low temperature	
Grade	KE-765-U	KE-785-U	KE-1265-U	KE-5615-U	KE-6080-U	KE-1734-U	KE-655-U	KE-503-U	KE-505-U	KE-136Y-U*3	KE-186-U	
Appearance	Pale yellow	Grayish white	Grayish white	White	Umber brown	Charcoal	Grayish white	White	Grayish white	Pale yellow	Milky white translucent	
Density 23°C g/cm ³	1.17	1.58	1.21	1.30	1.18	1.54	1.22	1.10	1.19	1.16	1.19	
Williams plasticity (10 min after remix)	270	370	230	300	270	420	300	170	210	220	250	
Curing agent	Curing agent name	C-8	C-8	C-23N	C-23N	C-23N	C-23N	C-8A	C-8	C-8	C-23N	C-23N
	Standard addition quantity*1	2.0	1.5	1.3	1.3	1.3	1.3	0.7	2.0	2.0	0.7	0.7
Linear shrinkage*2	%	3.7	2.4	—	—	—	—	3.8	4.0	3.4	3.6	—
Physical strength	Hardness Durometer A	63	83	66	62	55	74	60	32	48	52	61
	Tensile strength MPa	10.0	8.5	8.0	7.8	8.5	5.8	10.5	6.5	7.3	10.2	11.0
	Elongation at break %	340	110	280	330	390	140	400	650	330	620	690
	Tear strength crescent piece kN/m	—	—	12	11	13	13	28	18	19	32	34
Compression set 180°C x 22 h	8	11	—	—	—	17*9	15*7	15	17*10	16*11	—	
Dielectric breakdown strength Normal state	kV	27	26	28	28	27	28	24	23	29	—	
Volume resistivity Normal state	TΩ·m	10	10	51	70	80	50	50	8	200	—	
Remarks	Heat resistance		For general	Flame retardancy	High heat resistance	Flameretardancy Sintering	—	—	—	—	—	

Measurement: in accordance with JIS K 6249 Test pieces: 165°C x 10 min (press cure), 200°C x 4 h (post cure)

(Not specified values)

*1 Standard addition quantity is the quantity of curing agent added to 100 parts compound.

*2 Linear shrinkage values differ according to the curing agent used.

*3 Test pieces: 120°C x 10 min (press cure), 200°C x 4 h (post cure)

*4 Test pieces: 120°C x 10 min (press cure), 150°C x 1 h + 250°C x 24 h (post cure)

*5 Test pieces: 120°C x 10 min (press cure), 150°C x 1 h (post cure)

*6 Angle piece *7 Measured values at 150°C x 22 h *8 Ω·m *9 Measured values at 100°C x 22 h *10 Measured values at 150°C x 70 h *11 Measured values at 105°C x 70 h

[Unit conversion] tensile strength: 10 kgf/cm² = 0.98 MPa; tear strength: 1 kgf/cm = 0.98 kN/m; volume resistivity: 10¹⁴ Ω·cm = 1 TΩ·m.

Silicone rubber: other properties

Classification			For general purpose							Oil resistance
Grade			KE-941-U	KE-951-U	KE-961-U	KE-971-U	KE-981-U	KE-971T-U	KE-871C-U	
Heat resistance	Rate of change (RC) at 220°C x 96 h	Hardness Point	-4	-1	-1	+3	0	—	-2*1	
		Tensile strength %	-20	-10	-10	+2	-5	—	+9*1	
		Elongation at break %	-8	-22	-30	-35	-13	—	-10*1	
Oil resistance	RC at 150°C x 72 h IRM 903 Oil	Hardness Point	—	-15	-15	-15	—	-19	—	
		Tensile strength %	—	-25	-15	-15	—	-6	—	
		Elongation at break %	—	-30	-20	-10	—	-16	—	
		Volume change %	—	+30	+30	+26	—	+28	—	
	RC at 175°C x 70 h IRM 901 Oil	Hardness Point	—	—	—	-3	—	—	-7	
		Tensile strength %	—	—	—	+14	—	—	+7	
		Elongation at break %	—	—	—	-20	—	—	-3	
		Volume change %	—	—	—	+6	—	—	+5	
Flame retardance		UL94	HB	HB	HB	HB	HB	HB	—	
Low temperature characteristics		T10 Gehman test °C	—	-46	—	-47	—	—	—	

(Not specified values)

Classification			For general extrusion molding			Voltage resistance	Oil bleed	
Grade			KE-551-U*2	KE-561-U*2	KE-571-U*2	KE-655-U	KE-503-U	KE-505-U
Heat resistance	RC at 220°C x 96 h	Hardness Point	+4	+6	+8	+5*3	0*1	-4*1
		Tensile strength %	-19	-27	-28	-25*3	-5	-10*1
		Elongation at break %	-40	-41	-56	-30*3	-15	+8*1
Oil resistance	RC at 150°C x 72 h IRM 903 Oil	Hardness Point	—	—	—	-20	-10	—
		Tensile strength %	—	—	—	-40	-45	—
		Elongation at break %	—	—	—	-40	-50	—
		Volume change %	—	—	—	+55	+55	—

(Not specified values)

Classification			Flame retardance			Heat resistance		Hermetic heat resistance
Grade			KE-5620W-U	KE-5620BL-U	KE-5634-U	KE-552-U*4	KE-582-U*4	KE-552B-U*4
Heat resistance	RC at 220°C x 96 h	Hardness Point	+4	+3	—	+15*5	+8*5	+5
		Tensile strength %	+10	+13	—	-48*5	-35	-10
		Elongation at break %	-28	-28	—	-59*5	-60	-30
Flame retardance		UL94	V-0	V-0	V-1	—	—	—

Measurement: in accordance with JIS K 6249 Test pieces: 165°C x 10 min (press cure), 200°C x 4 h (post cure)

(Not specified values)

Classification			Steam resistance		
Grade			KE-7511-U	KE-7611-U	KE-7711-U
Heat resistance	RC at 220°C x 96 h	Hardness Point	+2*1	+3	+2*1
		Tensile strength %	-15	-10	-8*1
		Elongation at break %	-10	-15	-11*1

Measurement: in accordance with JIS K 6249 Test pieces: 165°C x 10 min (press cure), 200°C x 4 h (post cure)

(Not specified values)

*1 Measured values at 230°C x 72 h

*2 Relevant data id for addition cure (C-25A/B=0.5/2.0)

*3 Measured values at 200°C x 72 h

*4 Test pieces: 120°C x 10 min (press cure), 200°C x 4 h (post cure)

*5 Measured values at 300°C x 72 h

2. Fluorosilicone rubber

Fluorosilicone rubber is highly resistant to high and low temperatures and solvents, and has excellent workability. In IRM 903, a standard oil, there is less than 5% swelling (150°C x 70 h). Fluorosilicone rubber also has excellent resistance to silicone fluid. Shin-Etsu's fluorosilicone rubber products include the FE-201-U Series for general molding (hardness: 25-80), and the FE-301-U Series of high strength rubbers (hardness: 40-80). We also produce FE-451-U, a copolymer

type that exhibits oil resistance midway between that of dimethyl silicone rubber and fluorosilicone rubber. This copolymer material has oil resistance while also having superior cold resistance, and maintains a greater degree of rubber elasticity at low temperatures than typical silicone rubbers.

Applications: Rubber parts including diaphragms, check valves, and connectors, specifically in applications requiring oil and solvent resistance.

General properties

Grade		FE-251-U	FE-261-U	FE-271-U	FE-351-U	FE-361-U	FE-451-U*2
Appearance		Pale yellow	Pale yellow	Grayish white	Pale yellow	Pale yellow	Pale yellow
Density 23°C	g/cm ³	1.41	1.42	1.50	1.44	1.46	1.23
Prescribed curing agent	Curing agent name	C-8A	C-8A	C-8A	C-8A	C-8A	C-8A
	Standard addition quantity	0.8	0.8	0.8	0.8	0.8	0.8
Normal state data	Hardness Durometer A	54	63	73	49	62	50
	Elongation at break %	430	400	300	520	520	300
	Tensile strength MPa	9.8	9.8	9.0	13.3	12.7	6.4
	100% modulus MPa	1.9	2.7	5.3	0.98	1.2	1.8
	200% modulus MPa	4.4	5.8	6.6	2.5	2.7	3.7
	Tear strength Crescent kN/m	15	16	16	38	45	10
	Linear shrinkage %	3.5	3.5	3.3	3.3	3.2	3.8
	Rebound resiliency %	43	43	34	24	21	74
Heat resistance 200°C x 72 h	Compression set*1 %	8	8	9	17	14	6
	Hardness change Point	+2	+3	+3	+5	+5	+2
	Elongation change %	-7	-5	-16	±0	-2	-7
IRM 903 oil immersion 150°C x 70 h	Tensile strength change %	-16	-12	-17	-7	-8	-7
	Hardness change Point	-5	-5	-5	±0	±0	-11
	Elongation change %	-15	-5	-10	±0	+1	-18
	Tensile strength change %	-20	-10	-10	-2	±0	-19
Fuel C 25°C x 72 h	Volume change %	+4	+4	+4	+3	+3	+14
	Hardness change Point	-9	-9	-10	-12	-15	—
	Elongation change %	-44	-45	-23	-33	-14	—
	Tensile strength change %	-48	-40	-17	-46	-27	—
Remarks	Volume change %	+24	+23	+21	+23	+22	+140
	For fuel diaphragms and check valves			High tear strength			Copolymer

Measurement: based on JIS K 6249 Test pieces: 165°C x 10 min (press cure), 200°C x 4 h (post cure)

(Not specified values)

*1 Measured values at 180°C x 22 h *2 FE-451-U is produced in response to orders received.

3. SEP Rubber (silicone-modified EPDM)

SEP rubber is produced by modifying ethylene propylene rubber (EPDM) with silicone. This improves EPDM's properties of heat resistance and weather resistance, and low temperature characteristics. These performance characteristics lie between those of EPDM and silicone rubber, but SEP rubber has the additional favorable properties of chlorine resistance and sponge foaming characteristics. In high temperature conditions over 100°C, SEP rubber has higher mechanical strength, in particular tear

strength, than EPDM, and is comparable to high-strength silicone rubber. In terms of resistance to steam, hot water, acids and alkalis, SEP rubber is more durable than silicone rubbers. SEP rubbers are available in several grades: general grade (SEP-1411-U/SEP-1711-U), heat-resistant grade (SEP-1421-U/SEP-1721-U), extrusion grade (SEP-1731-U) and flame-resistant grade (SEP-363-U).

Applications: Rubber parts for high-temperature applications requiring high strength, including plug boots.

General properties

Grade		SEP-1411-U	SEP-1711-U	SEP-1421-U	SEP-1721-U	SEP-1731-U	SEP-363-U
Appearance		Pale yellow	Yellow	Pale yellow	Pale yellow	Gray	Black
Density 23°C g/cm ³		0.99	1.11	1.01	1.15	1.21	1.40
Prescribed curing agent	Curing agent name	C-12/SEP-BM	C-12	C-12	C-12	C-12/SEP-BM	C-12
	Standard addition quantity	2.0/0.1	2.0	2.0	2.0	4.0/0.2	1.5
Mooney viscosity ML 1+4 100°C		36	75	17	66	50	50
Normal state data	Hardness Durometer A	47	70	41	72	70	70
	Elongation at break %	820	600	930	550	600	400
	Tensile strength MPa	7.8	17.0	6.2	11.0	14.0	4.8
	Tear strength Crescent kN/m	12	35	12	30	30	25
	Rebound resiliency %	62	50	62	50	51	50
	Compression set* %	40	40	50	45	28	28
	Linear shrinkage %	—	2.5	—	2.7	—	—
Flame retardance	—	—	—	—	—	1.6 mm UL94 V-0	
Remarks		For general molding Sulfur cure possible	For general molding Sulfur cure possible	For general molding Heat-resistant grade	For general molding Heat-resistant grade	For extrusion General grade	Flame retardance Halogen-free

Measurement: based on JIS K 6249 Test pieces: 170°C x 10 min (press cure), 150°C x 2 h (post cure)

(Not specified values)

* Measured values at 150°C x 22 h

● We also offer a range of trial products in grades other than those listed above.

4. Curing agents

Shin-Etsu's silicone rubbers typically do not include a curing agent. These are called "U-types," and expressed such as KE-951-U. With U-type products, choose a suitable curing

agent (from C-1A to C-25A/B) in accordance with the curing method. We also offer curing agents other than those listed here. Please contact Shin-Etsu for details.

Types

Grade	Applications	Appearance	Main vulcanizing ingredient
C-1A	General molding, thin sections	White paste	Benzoyl peroxide Approx. 50% content
C-3	General molding, steam curing, flame retardance	White putty	Dicumyl peroxide Approx. 20% content
C-4	General molding	Grayish white paste	Ditertiarybutyl peroxide Approx. 20% content
C-8 C-8A C-8B	General molding, thick sections	Grayish white paste (C-8) Translucent paste (C-8A, C-8B)	2.5 dimethyl-2.5 bis (tertiarybutylperoxy) hexane Approx. 25% content (C-8), approx. 80% content (C-8A), approx. 40% content (C-8B)
C-12	SEP General molding, SEP Steam curing	White powder	Dicumyl peroxide Approx. 40% content
C-14	General molding, removed smell	Grayish white paste	Ditertiarybutyl peroxide Approx. 25% content
C-15	General molding, for transparent products	Translucent paste	2.5 dimethyl-2.5 bis (tertiarybutylperoxy) hexane Approx. 12.5% content
C-23N	Hot Air Vulcanization (HAV)	White paste	Paramethylbenzoylperoxide Approx. 50% content
C-25A/B	Vulcanization of addition-cure rubbers	Transparent paste (C-25A) Translucent paste (C-25B)	Contains metal complex (C-25A) Contains cross-linker (C-25B)

Suitability by application

Grade	Application					Curing method			
	Thin sections	Thick sections	Sponge*	Carbon compound products	Low compression set	HAV	CV	Mold	Coating
C-1A	●		●				●	●	●
C-3		●	●	●	●		●	●	
C-4		●			●			●	
C-8 C-8A C-8B	●	●		●	●		●	●	
C-14		●			●			●	
C-15	●	●		●	●			●	
C-23N			●			●	●	●	●
C-25A/B		●	●	●	●	●		●	

* Use sponge curing agents as a combination of C-1A with C-3, or C-23N with C-3.

Standard addition quantity

Grade	C-1A	C-3	C-4*1	C-8*2	C-8A	C-8B	C-15	C-23N
KE-931-U	0.75	3.2	4.0	2.0	0.5	1.0	—	1.8*
KE-941-U						1.0	—	
KE-951-U						1.0	—	
KE-961-U	0.6	2.3	3.5	2.0	0.4	1.0	—	1.4*
KE-971-U	0.55	1.9	3.0			1.0	—	1.3*
KE-981-U	0.5	1.6				1.0	—	1.2*
KE-961T-U	0.65	2.5	4.0	0.5	0.5	1.0	—	1.5
KE-971T-U	0.6	2.3	3.5			1.0	—	1.4
KE-871C-U	—	—	—	1.0	0.3	0.5	—	—
KE-9511-U	—	—	—	2.0	0.5	1.0	—	—
KE-5151-U	—	—	—	—	0.5	1.0	—	—
KE-5550-U	—	—	—	2.0	0.5	1.0	—	—
KE-501EM-U	—	—	—	—	—	—	1.5	—
KE-7211-U	—	1.3	—	—	—	—	—	—
KE-7212-U	—	1.3	—	—	—	—	—	—
KE-7213-U	—	—	—	2.0	0.5	1.0	—	—
X-30-3893-U	—	—	—	—	1.0	2.0	—	—
KE-9590-U	—	—	—	2.0	0.5	1.0	—	—
KE-541-U	0.8	3.0	4.0	2.0	0.6	1.0	—	1.0
KE-551-U								
KE-561-U	0.7	3.0	4.0	2.0	0.6	1.0	—	1.3
KE-571-U	0.6							
KE-581-U								
KE-153-U	C-25A/B=0.5/2.0							
KE-174-U								
KE-1551-U	0.8	3.2	4.0	2.0	0.5	1.0	—	0.8
KE-1571-U	0.7	2.0	3.0		0.4	1.0	—	0.7
KE-555-U*3	0.8	2.5	—	2.0	0.5	1.0	—	1.3
KE-575-U					0.4			

Grade	C-1A	C-3	C-4*1	C-8*2	C-8A	C-23N
KE-520-U	0.8	3.5	4.0	2.0	0.5	1.8*
KE-582-U		2.5	3.0	2.0	0.4	1.2
KE-552B-U		3.4	4.0		0.5	1.0
KE-7511-U	—	3.0	—	—	0.6	—
KE-7611-U		—	—	—		
KE-7711-U		—	—	—		
KE-3601SB-U	—	5.0	5.0	4.0	1.0	—
KE-3711-U		—	—	—		
KE-3801M-U		—	—	—		
KE-6801-U	0.5	2.0	3.0	2.0	0.4	0.8*
KE-765-U	0.7	2.8	3.0	2.0	0.5	1.3*
KE-785-U	0.6	2.6		1.5	0.4	1.2*
KE-1265-U	—	—	—	—	—	1.3
KE-5615-U	—	—	—	—	—	1.3
KE-6080-U	—	—	—	—	—	1.3
KE-1734-U	—	—	—	—	—	1.3
KE-655-U	—	3.0	4.0	2.0	0.7	—
KE-503-U	—	3.0	4.0	2.0	0.6	—
KE-505-U						
KE-136Y-U	0.75	3.0	—	2.0	0.5	0.7
KE-186-U	—	—	—	2.0	0.5	0.7

Standard addition quantity is the quantity of curing agent added to 100 parts compound.

★ Note: Please contact Shin-Etsu separately for information regarding Hot Air Vulcanization (HAV).

*1 C-4 is volatile, so the silicone rubber should be used soon after mixing.

*2 C-8 has qualities nearly identical to C-4, but has the advantage of lower volatility than C-4.

*3 Not available in U.S..

5. Standard conditions for compression molding

Grade	Thickness of molded item (mm)		Less than 1	1 - 5	5 - 10	10 - 25	25 - 50
	Press conditions						
C-1A* ¹ C-23N	Temperature	°C	120 - 125				
	Time	min	10	10 - 15	15 - 30	30 - 60	60 - 120
	Pressure	MPa	2.9 - 4.9				
C-3	Temperature	°C	155 - 160				
	Time	min	10	10 - 15	15 - 30	30 - 60	60 - 120
	Pressure	MPa	2.9 - 4.9				
C-4 C-14 C-8 C-15 C-8A C-8B	Temperature	°C	165 - 170				
	Time	min	10	10 - 15	15 - 30	30 - 60	60 - 120
	Pressure	MPa	2.9 - 5.9				
C-25A/B* ²	Temperature	°C	150 - 170				
	Time	min	10 - 20			20 - 60	60 - 120
	Pressure	MPa	2.9 - 5.9				

*1 Curing may be uneven in molded items thicker than 5 mm. Shin-Etsu recommends C-3, C-8, or C-8A for molding items over 5 mm thick.

*2 Molding possible at temperatures as low as 120°C-150°C.

6. Primers

By applying the primer in advance, better adhesion will be obtained.

Grade	Appearance	Ingredient (%)	Solvent	Drying conditions	Adherend
Primers No.4	Colorless, transparent	20	n-Heptane	23°C / 15 - 20 min	Metal, Plastic
Primers No.33	Reddish brown	20	Toluene/IPA	23°C x 30 min → 150°C x 15 min	Metal
Primers No.34-T	Colorless, transparent	20	Toluene/IPA	23°C x 30 min → 150°C x 15 min	Metal

● We offer other primers in addition to those listed above. Contact our Sales Department for details.

7. Coloring agents

Grade	Color	Coloring ingredient (%) (ingredient name)
KE-Color BR	Reddish brown	50 (iron oxide)
KE-Color W	White	50 (titanium oxide)
KE-Color MB	Blue	50 (lapis)
KE-Color BL	Black	50 (iron oxide, carbon)
KE-Color SB	Sky blue	50 (cobalt blue)
X-93-941	Yellow	50 (titanium oxide, organic pigment)
X-93-942	Red	50 (organic pigment)

8. Application examples by industry

Industry	Application examples	Desired properties	Typical grade
Home appliances	LED lamp holder	electrical insulation, heat resistance, flame retardance	KE-5620W-U
	defrosters	heat resistance, cold resistance, electrical insulation	KE-552B-U/KE-136Y-U/KE-582-U
	gaskets for refrigerators	cold resistance	KE-186-U
	hot airbrushes	heat resistance, weather resistance, color tone	KE-941-U/KE-951-U
	microwave oven window gaskets microwave oven turnbelts	heat resistance, low compression set	KE-552-U/KE-582-U
Electric power	lead wires of motors and electric appliances heater wires of rice cookers defroster wires of refrigerators ignition wires	electrical insulation, heat resistance, cold resistance, thermal conductivity, extrusion workability, flame retardance, high pressure-resistance	KE-552B-U*2
	connectors	dielectric strength	KE-7211-U/X-30-3893-U
Office equipment	keypads of mobile communications devices, etc.	electrical conductivity (some)*1, electrical insulation, flex fatigue resistance, low temperature-dependence	KE-951-U/KE-3711-U
	EMI gaskets	electrical conductivity, flame retardance, thermal conductivity	KE-3801M-U/KE-3711-U
Machinery	solar hoses	chlorine water resistance, weather resistance	KE-7511-U/KE-7611-U
	hot stamp rollers	heat resistance, low compression set	KE-765-U/KE-785-U
	vibration-damping rubbers	low rebound resilience	KE-5550-U*2/KE-501EM-U
Automotive	keypad	click property, fatigue durability	KE-9511-U/KE-5151-U
	diaphragms, o-rings	oil resistance, heat resistance, cold resistance, flex fatigue resistance	FE-251-U/FE-271-U
		oil resistance, heat resistance, JIS B2401 4-C for clack valves	KE-871C-U
	plug boots	oil resistance, heat resistance	KE-655-U
	waterproof connectors	heat resistance, oil bleed, oil resistance	KE-503-U/KE-505-U
	radiator hoses	heat resistance, cold resistance, low compression set, hot water resistance	SEP-1731-U
Construction	turbocharger hoses intercooler hoses	heat resistance, oil resistance, flex fatigue resistance	KE-552B-U/KE-655-U
	fire resistant gaskets	flame retardance, sinterability	KE-1734-U
Food	pressure cooker gaskets rice cooker and electric kettle gaskets electronic rice cooker gaskets	steam resistance, safety, chlorine water resistance low compression set	KE-971-U/KE-7611-U KE-7511-U/KE-961-U
	milkers	transparency, tear strength, safety, high strength	KE-153-U*2
	baby nipples	transparency, safety	KE-520-U
	lunch box gaskets	safety, low compression set	KE-951-U/KE-971-U
	cake mold, kitchenware	safety, coloring	*2
Leisure	swimming goggles, snorkel mouthpieces, goggle bands	transparency, high strength, high-class, safety, pleasant texture against the skin	KE-153-U

*1 Electrically conductive products such as KE-3711-U

*2 For information about these products, please contact one of the Sales Departments listed on the back cover.

Silicone Division Sales and Marketing Department III

6-1, Ohtemachi 2-chome, Chiyoda-ku, Tokyo, Japan

Phone : +81-(0)3-3246-5151 Fax : +81-(0)3-3246-5362

Shin-Etsu Silicones of America, Inc.

1150 Damar Drive, Akron, OH 44305, U.S.A.

Phone : +1-330-630-9860 Fax : +1-330-630-9855

Shin-Etsu do Brasil Representação de Produtos Químicos Ltda.

Rua Coronel Oscar Porto, 736 - 8º Andar - Sala 84,

Paraíso São Paulo - SP Brasil CEP: 04003-003

Phone : +55-11-3939-0690 Fax : +55-11-3052-3904

Shin-Etsu Silicones Europe B.V.

Bolderweg 32, 1332 AV, Almere, The Netherlands

Phone : +31-(0)36-5493170 Fax : +31-(0)36-5326459

(Products & Services: Products for cosmetics application)

Germany Branch

Rheingastrasse 190-196, 65203 Wiesbaden, Germany

Phone : +49-(0)611-962-5366 Fax : +49-(0)611-962-9266

(Products & Services: Products for industrial applications)

Shin-Etsu Silicone Taiwan Co., Ltd.

Hung Kuo Bldg. 11F-D, No. 167, Tun Hua N. Rd.,

Taipei, 10549 Taiwan, R.O.C.

Phone : +886-(0)2-2715-0055 Fax : +886-(0)2-2715-0066

Shin-Etsu Silicone Korea Co., Ltd.

GT Tower 15F, 411, Seocho-daero, Seocho-gu,

Seoul 06615, Korea

Phone : +82-(0)2-590-2500 Fax : +82-(0)2-590-2501

Shin-Etsu Singapore Pte. Ltd.

4 Shenton Way, #10-03/06, SGX Centre II, Singapore 068807

Phone : +65-6743-7277 Fax : +65-6743-7477

Shin-Etsu Silicones India Pvt. Ltd.

Unit No. 403A, Fourth Floor, Eros Corporate Tower,

Nehru Place, New Delhi 110019, India

Phone : +91-11-43623081 Fax : +91-11-43623084

Shin-Etsu Silicones (Thailand) Ltd.

7th Floor, Harindhorn Tower, 54 North Sathorn Road, Bangkok 10500, Thailand

Phone : +66-(0)2-632-2941 Fax : +66-(0)2-632-2945

Shin-Etsu Silicone International Trading (Shanghai) Co., Ltd.

29F Junyao International Plaza, No.789,

Zhao Jia Bang Road, Shanghai 200032, China

Phone : +86-(0)21-6443-5550 Fax : +86-(0)21-6443-5868

Guangzhou Branch

Room 2409-2410, Tower B, China Shine Plaza, 9 Linhexi Road,

Tianhe, Guangzhou, Guangdong 510610, China

Phone : +86-(0)20-3831-0212 Fax : +86-(0)20-3831-0207

- The data and information presented in this catalog may not be relied upon to represent standard values. Shin-Etsu reserves the right to change such data and information, in whole or in part, in this catalog, including product performance standards and specifications without notice.
- Users are solely responsible for making preliminary tests to determine the suitability of products for their intended use. Statements concerning possible or suggested uses made herein may not be relied upon, or be construed, as a guaranty of no patent infringement.
- The silicone products described herein have been designed, manufactured and developed solely for general industrial use only; such silicone products are not designed for, intended for use as, or suitable for, medical, surgical or other particular purposes. Users have the sole responsibility and obligation to determine the suitability of the silicone products described herein for any application, to make preliminary tests, and to confirm the safety of such products for their use.
- Users must never use the silicone products described herein for the purpose of implantation into the human body and/or injection into humans.
- Users are solely responsible for exporting or importing the silicone products described herein, and complying with all applicable laws, regulations, and rules relating to the use of such products. Shin-Etsu recommends checking each pertinent country's laws, regulations, and rules in advance, when exporting or importing, and before using the products.
- Please contact Shin-Etsu before reproducing any part of this catalog. Copyright belongs to Shin-Etsu Chemical Co., Ltd.



The Development and Manufacture of Shin-Etsu Silicones are based on the following registered international quality and environmental management standards.

Gunma Complex ISO 9001 ISO 14001
(JCQA-0004 JCQA-E-0002)

Naoetsu Plant ISO 9001 ISO 14001
(JCQA-0018 JCQA-E-0064)

Takefu Plant ISO 9001 ISO 14001
(JQA-0479 JQA-EM0298)

"Shin-Etsu Silicone" is a registered trademark of Shin-Etsu Chemical Co., Ltd. <https://www.shinetsusilicone-global.com/>