

High Heat Resistant Silicone Rubber

X-30-3888-U, X-30-4574-U

Millable Molded Silicone Rubber Excellent in Rubber Properties in High Temperature

High heat resistance

Compression molding

Extrusion molding

Colorability

Wide range rubber hardness

UL94HB equivalent



Features

- Even in a high temperature 250-300 degrees, the physical property change is small and hardly deteriorated.
- It has extremely high heat resistance and can be used at 350 degrees for short periods of time.
- Wide lineup of hardness up to 40-80.

Applications

Hoses, tubes, electric wires, gaskets, and other rubber parts that require high heat resistance



General properties

Grade		High heat resistant product	Colorable high heat resistant product	Conventional product
Product name		X-30-3888-U	X-30-4574-U	KE-552D-U
Appearance		Dark brown	Ivory	Pale yellow
Plasticity		264	250	—
Curing agent	Curing agent name	C-23N	C-23N	C-23N
	Standard addition quantity	1.3	1.3	1.3
Standard molding condition	Primary cure	120°C × 10 min	120°C × 10 min	120°C × 10 min
	Post cure	150°C × 1 h	150°C × 1 h	150°C × 1 h
Hardness		55	57	60
Density at 23°C g/cm ³		1.19	1.15	1.15
Tensile strength MPa		9.1	8.5	9.3
Elongation at break %		360	310	310
Heat resistant 300°C × 72 h	Hardness change	±0	+2	+15
	Tensile strength change %	66	70	51
	Retention of elongation at break %	85	90	30
Rubber hardness lineup Durometer A		40 - 80	40 - 80	—


(Not specified values)

High Heat Resistant Silicone Rubber

X-30-3888-U, X-30-4574-U

Test result

The high heat resistant silicone rubber compound X-30-3888-U has little change in hardness, elongation, and the like even in a high temperature range of 300 degrees.



* This value is not a specification value or guaranteed value.

* This value is not a specification value or guaranteed value.

Handling precautions

1. Silicone rubber may react with strong oxygen agents.
2. Uncured substance generates silica. Please handle with caution.

Safety and hygiene

1. This product causes serious eye irritation and may cause skin irritation. When handling the product, be sure to avoid contact with the skin and mucous membranes by wearing protective glasses and protective gloves. In case of skin contact, immediately wipe off with dry cloth and then flush thoroughly with running water. In case of accidental eye contact, flush immediately with plenty of clean water

for at least 15 minutes and then seek medical attention. Contact lens wearers must take special care. If the products get into the eye, the contact lens may become stuck to the eye.

2. In a confined space with poor ventilation, please wear a protective mask. It is recommended to provide local ventilation. If vapors are inhaled and victims feel uncomfortable, move immediately to an area with fresh air. When you put non-hardening substance into the discard, silica and other powder generate. So you should wear a protective mask.
3. Keep out of reach of children.
4. Please read the Safety Data Sheets (SDS) before use. SDS can be obtained from our Sales Department.

•The data and information presented in this catalog may not be relied upon to represent standard values. Shin-Etsu reserves the right to change such data and information, in whole or in part, in this catalog, including product performance standards and specifications without notice.

•Users are solely responsible for making preliminary tests to determine the suitability of products for their intended use. Statements concerning possible or suggested uses made herein may not be relied upon, or be construed, as a guaranty of no patent infringement.

•For detailed information regarding safety, please refer to the Safety Data Sheet (SDS).

•The silicone products described herein have been designed, manufactured and developed solely for general industrial use only; such silicone products are not designed for, intended for use as, or suitable for, medical, surgical or other particular purposes. Users have the sole responsibility and obligation to determine the

suitability of the silicone products described herein for any application, to make preliminary tests, and to confirm the safety of such products for their use.

•Users must never use the silicone products described herein for the purpose of implantation into the human body and/or injection into humans.

•Users are solely responsible for exporting or importing the silicone products described herein, and complying with all applicable laws, regulations, and rules relating to the use of such products. Shin-Etsu recommends checking each pertinent country's laws, regulations, and rules in advance, when exporting or importing, and before using the products.

•Please contact Shin-Etsu before reproducing any part of this catalog. Copyright belongs to Shin-Etsu Chemical Co., Ltd.

Shin-Etsu

Shin-Etsu Chemical Co., Ltd.
Silicone Division Sales and Marketing Department III
Phone : +81-(0)3-6812-2408 Fax : +81-(0)3-6812-2415

<https://www.shinetsusilicone-global.com/>

■ Overseas sales office is here.

www.shinetsusilicone-global.com/globalnetwork/

